

Starcret universal filler



Ready-to-use cement-based dry mix, plastic-modified. For repairs, coatings and for smoothing, levelling concrete, plaster and mortar. Especially for exposed concrete cosmetics for interior and exterior use. Grain size 0 - 0.3 mm

High flexural strength (see strength tables)
Consistent quality and colour (concrete light, without colour pigments)

Consumption

Consumption:

15 kg dry mortar yields approx. 7.5 litres fresh mortar. Layer thickness 1.5 - 5 mm per working step

Processing

Processing:

The substrate must be cleaned and pre-wetted. The water requirement is approx. 3.3 l per 15 kg bucket. Mix until a spatula-like consistency is achieved. Processing time approx. 60 minutes at 20°C

Technical data

Strength tables

1 day 3 days 7 days 28 days Compressive strength N/mm2 5.8 21 28 Flexural strength N/mm2 1.9 3.7 5.8

Article description	Title of variant	Packaging piece/pallet	Weight kg/bucket
19027015	Starcret universal filler	1-24 bucket/pallet	15